

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
13 March 2003 (13.03.2003)


PCT

(10) International Publication Number  
**WO 03/020638 A1**

- (51) International Patent Classification<sup>7</sup>: C01B 31/02, A61K 9/70, B05D 3/10, G03F 7/038, C08K 3/04, C08L 77/00, C08K 5/01, C01B 31/00
- (74) Agent: GOODMAN, Kenneth, D.; Williams, Morgan & Emerson, P.C., Suite 1100, 10333 Richmond, Houston, TX 77042 (US).
- (21) International Application Number: PCT/US02/27370
- (22) International Filing Date: 27 August 2002 (27.08.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
60/315,583 29 August 2001 (29.08.2001) US
- (71) Applicant: GEORGIA TECH RESEARCH CORPORATION [US/US]; Centennial Research Building, 505 10th Street, Atlanta, GA 30332-0415 (US).
- (72) Inventors: KUMAR, Satish; 2349 Lake Forest Trail, Lawrenceville, GA 30043 (US). ARNOLD, Fred, E.; 1583 Ambridge Road, Centerville, OH 45459 (US). DANG, Thuy, D.; 6195 Millbank Drive, Centerville, OH 45459 (US).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:  
— with international search report

[Continued on next page]

(54) Title: COMPOSITIONS COMPRISING RIGID-ROD POLYMERS AND CARBON NANOTUBES AND PROCESS FOR MAKING THE SAME



(57) Abstract: The present invention relates to compositions comprising rigid-rod polymers and carbon nanotubes. The compositions comprise dispersed carbon nanotubes aligned with rigid-rod polymers. The alignment of the nanotubes and polymers can be liquid crystalline. The rigid-rod polymers of this invention include, but are not limited to, polymers and copolymers comprising benzobisazole, pyridobisimidazole and benzamidazobenzophenanthroline repeat units. Dispersion of carbon nanotubes is achieved by in-situ polymerization in the presence of the carbon nanotubes, which may be either single-wall or multi-wall or a combination of both. The polymer compositions comprising carbon nanotubes may be spun into fibers or formed into films. The strength of the resulting fibers of the present invention is significantly greater than that of fibers without carbon nanotubes.

WO 03/020638 A1



*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

**COMPOSITIONS COMPRISING RIGID-ROD POLYMERS AND CARBON  
NANOTUBES AND PROCESS FOR MAKING THE SAME**

This invention was made with United States Government support under Grant  
5 No. F49620-00-1-0147 awarded by the United States Air Force. Government may have  
certain rights in the invention.

**BACKGROUND OF THE INVENTION**

Single-wall carbon nanotubes (SWNT) are fullerenes of closed-cage carbon  
10 molecules typically arranged in hexagons and pentagons. These carbon cylindrical  
structures, known commonly as "buckytubes", have extraordinary properties, including both  
high electrical and thermal conductivity, as well as high strength and stiffness. For  
background information on single-wall carbon nanotubes see B.I. Yakobson and R. E.  
Smalley, *American Scientist*, Vol. 85, July-August, 1997, pp. 324-337.

15 Nested single-wall carbon cylinders, known as multi-wall carbon nanotubes  
(MWNT), possess some properties similar to single-wall carbon nanotubes, however, since  
single-wall carbon nanotubes have fewer defects than multi-wall carbon nanotubes, the  
single-wall carbon nanotubes are generally stronger and more conductive.

To exploit the exceptional strength and conductive properties of carbon nanotubes,  
20 numerous attempts have been made to incorporate carbon nanotubes into polymers.  
However, one of the problems encountered in making polymer-nanotube composite blends is  
the difficulty in achieving a good dispersion of the nanotubes. The better the nanotube  
dispersion, the more the strength properties of the nanotubes will be conveyed to the polymer  
composite.

25 Carbon nanotubes, especially single-wall carbon nanotubes, once in contact, tend to  
be held tightly together by van der Waals forces. Dispersing single-wall carbon nanotubes is  
even more difficult than dispersing multi-wall nanotubes because the single-wall carbon  
nanotubes can "rope" together in aligned bundles of a few to many hundreds of nanotubes.  
In order to obtain a good nanotube dispersion, van der Waals forces which hold the  
30 nanotubes together must be overcome. Means to separate the nanotubes in intimate contact  
with each other, such as by sonication, can also damage the nanotubes and, consequently,  
impair strength and tensile properties.

Thus, there is a need for polymer composites comprising carbon nanotubes wherein  
the nanotubes are well dispersed in the polymer. There is also a need for high strength fibers

for applications in articles such as bullet-proof vests, body armor, vehicular armor, ballistic protection equipment, and as reinforcing fibers for both organic and inorganic products, such as in tires, belts, ceramics, polymer laminates for aircraft and other compositions requiring high strength materials. Likewise, there is a need for a method for preparing polymer composites comprising carbon nanotubes wherein the carbon nanotubes are well-dispersed and wherein the structure and properties of the nanotubes have not been adversely affected.

### SUMMARY OF THE INVENTION

The present invention relates to new polymer compositions comprising rigid-rod polymers and carbon nanotubes. The carbon nanotubes of this invention include both single-wall carbon nanotubes and multi-wall carbon nanotubes. Single-wall carbon nanotubes are considered to be the most rigid tubular polymeric material in existence with the highest tensile properties. (See B.I. Yakobson and R. E. Smalley, *American Scientist*, Vol. 85, July-August, 1997, pp. 324-337.)

Rigid-rod polymers are also characterized by high tensile strength, high modulus, stiffness and thermal stability. Such polymers are also referred to as liquid crystal extended chain polymers. Particularly useful are compositions comprising rigid-rod heterocyclic aromatic polymers and copolymers comprising benzobisazole, pyridobisazole and/or benzamidazobenzophenanthroline repeat units. In this application, rigid-rod polymers shall be defined as those polymers comprising benzobisazole, pyridobisazole and/or benzamidazobenzophenanthroline repeat units, and shall include copolymers, comprising at least one different monomer repeat unit, and substituted polymers and copolymers, wherein other chemical moieties or functional groups are substituted on the benzobisazole, pyridobisazole and/or benzamidazobenzo-phenanthroline repeat units.

This invention also relates to a method of forming polymer composites comprising well-dispersed carbon nanotubes by in-situ polymerizing a rigid-rod polymer or copolymer in the presence of carbon nanotubes. In the polymerization, rigid-rod polymers or copolymers are formed and generally align in an anisotropic, liquid crystal distribution. The propagating rigid-rod polymer or copolymer acts as a template for ordering the carbon nanotubes. As the rigid-rod polymer or copolymer orders into liquid crystalline domains, the polymer or copolymer entraps the carbon nanotubes in the liquid crystalline solution or dope. These polymer-nanotube compositions are extremely suitable for spinning into highly ordered and high strength fibers which exhibit significantly improved tensile properties over fibers spun without nanotubes. Likewise, formation of composite rigid-rod polymer/nanotube films also

results in films with significantly improved strength properties over the films without nanotubes.

### BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 shows typical stress-strain curves for PBO and PBO/SWNT (90/10) fibers.

Figure 2 shows thermal shrinkage at 25 MPa stress in PBO and PBO/SWNT (90/10) fibers when heated at 10 °C per minute in nitrogen


Figure 3 shows creep behavior of PBO and PBO/SWNT (90/10) fibers at 400 °C at a stress of 250 MPa.

Figure 4 shows weight loss in PBO, PBO/SWNT (90/10), and SWNT when heated at 20°C/minute in nitrogen.


### DESCRIPTION OF ILLUSTRATIVE EMBODIMENTS

This invention provides a composition comprising a dispersion of carbon nanotubes in rigid-rod polymers or copolymers. In the scope of this invention, the term "polymers" shall also include "copolymers". The invention also provides a method for producing polymer compositions comprising carbon nanotubes and rigid-rod polymers and copolymers. The method involves in-situ polymerization of rigid-rod polymers in the presence of carbon nanotubes. The carbon nanotubes may be either single-wall, multi-wall or a combination thereof. The in-situ polymerization is done through the polycondensation of diamines and diacid monomers in the presence of carbon nanotubes. As the rigid-rod polymers or copolymers polymerize, liquid crystalline domains form. The nanotubes align along the propagating para-ordered rigid-rod molecules and are entrapped in the resulting dope. The resulting anisotropic alignment of the rigid-rod polymers and carbon nanotubes appears liquid crystalline in nature. The present invention provides a substantially uniform, aligned distribution of nanotubes that is not readily obtainable by the process of melt mixing a molten polymer with carbon nanotubes.

Processing of the new compositions into fibers and films provides hybrid materials with vastly improved tensile properties, which are superior to the same polymers without incorporated nanotubes. Although not meaning to be limited, the polymer component of the present compositions can include various benzobisazole, pyridobisimidazole, and benzamidazobenzophenanthroline polymers and copolymers. Fibers of these polymers and copolymers are known for their extremely high modulus and high strength. Rigid rod polymers and copolymers based on benzobisazole include the repeating group:



or




5


where Y is -O-, -S- or -NR', where R' is -H, alkyl having 1 to 4 carbon atoms, or an aromatic group having 1 or 2 aromatic rings.

10

Examples of rigid-rod benzobisazole polymers include para-ordered heterocyclic polymer having a repeat group of the formula



or




15


wherein Y is -S-, n is 1 or 2, and R is a hydroxyl group, a sulfo group or an alkyl group having 1 to 4 carbon atoms.

20

Other examples of rigid rod polymers include benzimidazole polymers and copolymers comprising repeat units of the formula




or




5

and include p-phenylenebenzimidazole (PBI) comprising repeat units of the formula




10

Such polymers and copolymers are described in U.S. Pat. No. 3,901,855 and incorporated by reference herein in its entirety. Further examples of benzobisazole polymers are polybenzobisoxazole polymers and copolymers comprising repeat units of the formula




or




15


and include polymers and copolymers of p-phenylenebenzobisoxazole (PBO) comprising repeat units of the formula



Further examples of benzobisazole polymers include polymers and copolymers of polybenzobisthiazole comprising repeat units of the formula




and include polymers and copolymers of p-phenylenebenzobisthiazole (PBZT) comprising repeat units of the formula




both described in U.S. Pat. No. 4,533,693, incorporated by reference herein in its entirety.

Further examples of benzobisazole polymers and copolymers are those p-phenylenebenzobisazole polymers and copolymers containing pendant substituents on the phenylene group, including phenylenebenzobisazoles with pendant hydroxyl groups, such as dihydroxyphenylene-benzobisoxazole (Di-OH PBO), comprising repeat units of the formula






dihydroxy-phenylenebenzobisimidazole (Di-OH PBI) comprising repeat units of the formula




5

dihydroxyphenylenebenzobisthiazole (Di-OH PBZT), comprising repeat units of the formula




10

described in U.S. Pat. Nos. 5,041,522 and 5,039,778, each incorporated by reference herein in its entirety, and dihydroxyphenylenepyridobisimidazole (Di-OH PPBI) comprising repeat units of the formula




15


and described in U.S. Pat. No. 5,674,969, incorporated by reference herein in its entirety, polymers and copolymers of phenylenebenzobisazoles having pendant sulfo groups, such as sulfo-phenylenebenzobisoxazole (sulfo-PBO) comprising repeat units of the formula




sulfopolybenzobisimidazole (sulfo-PBI), comprising repeat units of the formula



and sulfo-phenylenebenzobisthiazole (sulfo-PBZT), comprising repeat units of the formula




described in U.S. Pat. Nos. 5,312,876 and 5,312,895, each incorporated by reference herein in its entirety, polymers and copolymers phenylenebenzobisazole with pendant methyl groups, such as methyl- and dimethylphenylenebenzobisoxazole (Me-PBO) comprising repeat units of the formula




where R and R' = CH<sub>3</sub> or where R = CH<sub>3</sub> and R' = H

methyl- and dimethyl-phenylenebenzobisimidazole (Me-PBI), comprising repeat units of the formula




where R and R' = CH<sub>3</sub> or where R = CH<sub>3</sub> and R' = H

5 and methyl- and dimethyl-phenylenebenzobisthiazole (Me-PBZT), comprising repeat units of the formula



10 where R and R' = CH<sub>3</sub> or where R = CH<sub>3</sub> and R' = H

described in U.S. Pat. Nos. 5,000,217, 5,098,988 and 5,136,012, each incorporated by reference herein in its entirety. Another example of rigid rod polymers include polymers and copolymers of benzamidazobenzophenanthroline (BBL) comprising repeat units of the  
15 formula



described in U.S. Pat. No. 3,632,414, incorporated by reference herein in its entirety.

20 In this invention, the rigid rod polymers and copolymers, such as those based on benzobisazoles, pyridobisazoles and benzamidazobenzophenanthroline, are formed in-situ from the polycondensation of diamine and diacid monomers. Suitable amino-group-

containing monomers include, but are not limited to: 2,5-diamino-1,4-benzenedithiol dihydrochloride, 4,6-diamino-1,3-benzenediol dihydrochloride, 1,2,4,5-tetraaminobenzene tetrahydrochloride, 2,3,5,6-tetraaminopyridine tetrahydrochloride, 2,5-diamino-1,4-benzenediol dihydrochloride, and 1,4,5,8-tetraaminonaphthalene tetrahydrochloride. Suitable acid-group-containing monomers include, but are not limited to: terephthalic acid, mono- and dihydroxy-terephthalic acid, 2-sulfoterephthalic acid, 1,4,5,8-tetracarboxynaphthalene, 2-methylterephthalic acid, 2,5-dimethyl-terephthalic acid, 1,5-dicarboxynaphthalene, and 2,6-dicarboxynaphthalene.

The in-situ polymerizations may be conducted in any suitable medium in which the rigid-rod polymers can be formed and maintained in solution. A suitable medium for carrying out the polycondensation polymerizations of the present invention comprises polyphosphoric acid (PPA), having a formula represented by  $H_{n+2}P_nO_{3n+1}$  or  $HO-(PO_3H)_n-H$ . The polyphosphoric acid composition can be expressed in terms of the phosphorous pentoxide ( $P_2O_5$ ) content or the phosphoric acid ( $H_3PO_4$ ,  $n = 1$ ) content.

The polymer concentration in the medium preferably is selected to promote the formation of an anisotropic reaction mixture. Polymer concentrations in the range from about 1 wt% to about 20 wt% in the medium can promote an anisotropic reaction mixture. The carbon nanotube concentration preferably can range from about 0.1 wt% to about 50 wt%, more preferably from about 1 wt% to about 30 wt% based on the weight of polymer in the polymerization.

In the present invention, the process for making a rigid-rod polymer/nanotube composition involves synthesizing the rigid-rod polymer or copolymer in the presence of carbon nanotubes. In one embodiment of in-situ polymerization, stoichiometric amounts of amine hydrochloride and acid monomers are combined in 85% phosphoric acid and heated to a temperature in the range of about 60° to about 80°C to effect the thermal dehydrochlorination of the amine monomer. Note that the use of amines without protective hydrochloride is also within the scope of this invention. After the dehydrochlorination is complete, the nanotubes are added. The temperature is then raised to about 100°C and maintained for about 4 to 6 hours. The reaction temperature is cooled to about 45°C and phosphorous pentoxide ( $P_2O_5$ ) is added to make 77% PPA. After the phosphorous pentoxide addition, the temperature is increased to 100°C and maintained for about 4 hours. Additional  $P_2O_5$  is then added to increase the PPA concentration to about 82 to about 84% PPA. The temperature is then raised to about 165°C and maintained at that temperature for about 10 to 12 hours. The temperature of the reaction mixture is then raised to about 190°C and held for

about 4 hours. The procedure results in a liquid crystalline composition comprising rigid-rod liquid crystalline polymer and nanotubes that can be extruded and processed into fiber or film.

After each in-situ polymerization, aliquot samples are taken to determine intrinsic viscosity and also for processing into cast films. The samples are precipitated into water, treated with ammonium hydroxide, washed extensively with water, and dried under reduced pressure. After precipitating into water or redissolving of dried samples in methanesulfonic acid for intrinsic viscosity measurements, the samples show no separation of the nanotubes from the derived polymer.

Fiber spinning may be done by any suitable technique. One such method is dry-jet wet spinning using a piston driven spinning system. For fiber spinning, the polymer solution or dope comprising the rigid-rod polymer, nanotubes and phosphoric acid medium preferably is maintained between about 100°C and about 150°C. An air gap preferably is maintained in the range of about 2 cm and about 25 cm. Extruded fiber is coagulated in water at room temperature. Fiber is washed in running water for about a week or for any time sufficient to remove the acid from the fiber. The fiber is subsequently dried in vacuum at about 80°C. Dried fiber can be heat-treated in nitrogen at about 400°C to impart higher strength and tensile properties. Generally, the fibers of the present invention comprising rigid-rod polymer/carbon nanotube composites have significantly higher strength and tensile properties, such as higher stiffness, tensile modulus, and strain to failure (elongation to break), than like polymer fibers without nanotubes. Certain fibers comprising the rigid-rod polymers/nanotube composites of this invention have shown about 50% greater tensile strength than over fibers of the same polymeric composition without nanotubes. Fibers prepared with the compositions of this invention also show lower creep than like polymer fibers without carbon nanotubes.

This composite of this invention provides a fundamental improvement in products and articles of manufacture comprising rigid-rod polymers and copolymers, and it enables new and improved articles of manufacture, including, but not limited to composite structural materials, films, coatings and fibers requiring high tensile strength such as for high-strength fibers and structural elements of machines, buildings, and vehicles. Improved articles of manufacture incorporating fibers of the present invention include body armor, bullet-proof vests, vehicular armor, armor for structures, elements of ballistic protection systems and as reinforcing fibers for both organic and inorganic products, such as in tires, belts, ceramics,

polymer laminates for aircraft and other compositions requiring high strength materials. Depending on the nanotube concentration and dispersion, additional properties of electrical or thermal conductivity, electromagnetic and radio-frequency shielding may also be realized.

5       The following examples are included to demonstrate preferred embodiments of the invention. It should be appreciated by those of skill in the art that the techniques disclosed in the examples which follow represent techniques discovered by the inventor to function well in the practice of the invention, and thus can be considered to constitute preferred modes for its practice. However, those of skill in the art should, in light of the present disclosure, appreciate that many changes can be made in the specific embodiments which are disclosed  
10       and still obtain a like or similar result without departing from the spirit and scope of the invention.

#### EXAMPLE I

##### 15       PBZT/SWNT (95/5)

A composition of 5% single-wall carbon nanotubes (SWNT) and 95% polyphenylenebenzobisthiazole (PBZT) was prepared as follows. Into the bottom of a 250-ml resin flask equipped with a mechanical stirrer, a nitrogen inlet and outlet, was placed 4.904 g (0.02 mol) of 2,5-diamino-1,4-benzenedithiol dihydrochloride, 3.3226 g (0.02 mol)  
20       of terephthalic acid, and 20.68 g of phosphoric acid (85%). The resulting mixture was dehydrochlorinated under nitrogen atmosphere at 65°C for 16 hours. The temperature was then raised to 80°C and held for 4 hours. 0.26 g of purified single-wall carbon nanotubes (HiPco™ single-wall carbon nanotubes from Carbon Nanotechnologies, Inc., Houston, TX, purified according to the procedures given in I.W. Chiang, *et al.*, *J. Phys. Chem.*, Vol. 105,  
25       2001, p. 8297) was added to the mixture and heated at 100°C for 16 hours. The mixture was then cooled the mixture to room temperature. 13.69 g P<sub>2</sub>O<sub>5</sub> was added to the mixture to generate polyphosphoric acid (77% P<sub>2</sub>O<sub>5</sub>). The mixture was stirred for 2 hours at 80°C and cooled to room temperature. 12.13 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to bring the polymer concentration to 10%. The mixture was heated at 160°C for 16 hours. As the temperature  
30       increased, stir opalescence began to occur at about 150°C. The mixture was finally heated to 190°C for an additional 4 hours. An aliquot of the polymer dope was precipitated in water, broken up with a blender, collected by suction filtration, washed with water and dried under

reduced pressure (0.02 mm Hg) at 100°C for 24 hours. An intrinsic viscosity of 17 dl/g was determined in methanesulfonic acid at 30°C.

## EXAMPLE II

### PBZT/MWNT (90/10)

A composition of 10% multi-wall carbon nanotubes (MWNT) and 90% polyphenylenebenzobisthiazole (PBZT) was prepared as follows. Into the bottom of a 250-ml resin flask equipped with a mechanical stirrer, a nitrogen inlet and outlet, was placed 4.904 g (0.02 mol) of 2,5-diamino-1,4-benzenedithiol dihydrochloride, 3.3226 g (0.02 mol) of terephthalic acid, and 20.68 g of phosphoric acid (85%). The resulting mixture was dehydrochlorinated under nitrogen atmosphere at 65°C for 16 hours. The temperature was then raised to 80°C and held for 4 hours. 0.52 g of multi-wall carbon nanotubes (Pyrograph PR-24-HT carbon nanofiber grade from Applied Sciences, Inc., Cedarville, OH) was added to the mixture. The mixture was heated at 100°C for 16 hours and then cooled the mixture to room temperature. 13.69 g P<sub>2</sub>O<sub>5</sub> was added to the mixture to generate polyphosphoric acid (77% P<sub>2</sub>O<sub>5</sub>). The mixture was stirred for 2 hours at 80°C and then cooled to room temperature. 12.13 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to bring the polymer concentration to 10%. The mixture was heated at 160°C for 16 hours. As the temperature increased, stir opalescence began to occur at about 150°C. The mixture was finally heated to 190°C and held for an additional 4 hours. An aliquot of the polymer dope was precipitated in water, broken up with a blender, collected by suction filtration, washed with water and dried under reduced pressure (0.02 mmHg) at 100°C for 24 hours. An intrinsic viscosity of 28 dl/g was determined in methanesulfonic acid at 30°C.

## EXAMPLE III

### PBO/SWNT (95/5)

A composition of 5% single-wall carbon nanotubes (SWNT) and 95% polyphenylenebenzobisoxazole (PBO) was prepared as follows. Into the bottom of a 250-ml resin flask equipped with a mechanical stirrer, a nitrogen inlet and outlet, was placed 4.2612 g (0.02 mol) of 1,4-diaminoresorcinol dihydrochloride, 4.0605 g (0.02 mol) of terephthaloyl chloride, and 12.14 g of phosphoric acid (85%). The resulting mixture was dehydrochlorinated under nitrogen atmosphere at 65°C for 16 hours. The temperature was then raised to 80°C and held for 4 hours. 0.234 g of purified single-wall carbon nanotubes

(HiPco™ single-wall carbon nanotubes from Carbon Nanotechnologies, Inc., Houston, TX, purified according to the procedures given in I.W. Chiang, *et al.*, *J. Phys. Chem.*, Vol. 105, 2001, p. 8297) was added to the mixture. The mixture was heated at 100°C for 16 hours and then cooled to room temperature. 8.04 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to generate polyphosphoric acid (77% P<sub>2</sub>O<sub>5</sub>). The mixture was stirred for 2 hours at 80°C and then cooled to room temperature. 7.15 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to bring the polymer concentration to 14%. The mixture was heated at 160°C for 16 hours. As the temperature increased, stir opalescence began to occur at about 155°C. The mixture was finally heated to 190°C for an additional 4 hours. An aliquot of the polymer dope was precipitated in water, broken up with a blender, collected by suction filtration, washed with water and dried under reduced pressure (0.02 mmHg) at 100°C for 24 hours. An intrinsic viscosity of 14 dl/g was determined in methanesulfonic acid, at 30°C.

#### EXAMPLE IV

##### PBO/SWNT (90/10)

A composition of 10% single-wall carbon nanotubes (SWNT) and 90% polyphenylenebenzobisoxazole (PBO) was prepared as follows. Into the bottom of a 250-ml resin flask equipped with a mechanical stirrer, a nitrogen inlet and outlet, was placed 4.2612 g (0.02 mol) of 1,4-diaminoresorcinol dihydrochloride, 4.0605 g (0.02 mol) of terephthaloyl chloride, and 12.14 g of phosphoric acid (85%). The resulting mixture was dehydrochlorinated under nitrogen atmosphere at 65°C for 16 hours. The temperature was then raised to 80°C and held for 4 hours. 0.47 g of purified SWNT (HiPco™ single-wall carbon nanotubes from Carbon Nanotechnologies, Inc., Houston, TX, purified according to the procedures given in I.W. Chiang, *et al.*, *J. Phys. Chem.*, Vol. 105, 2001, p. 8297) tubes was added to the mixture. The mixture was heated at 100°C for 16 hours and then cooled the mixture to room temperature. 8.04 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to generate polyphosphoric acid (77% P<sub>2</sub>O<sub>5</sub>). The mixture was stirred for 2 hours at 80°C and then cooled to room temperature. 7.15 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to bring the polymer concentration to 14%. The mixture was heated at 160°C for 16 hours. As the temperature increased, stir opalescence began to occur at about 155°C. The mixture was finally heated to 190°C and held for an additional 4 hours.

No SWNT aggregates were observed in optical micrographs taken of the PBO/SNWT dope under cross polarizers, indicating good nanotube dispersion at the optical scale during



PBO polymerization. An aliquot of the polymer dope was precipitated in water, broken up with a blender, collected by suction filtration, washed with water and dried under reduced pressure (0.02 mmHg) at 100°C for 24 hours. An intrinsic viscosity of 14 dl/g was determined in methanesulfonic acid, at 30°C.

#### EXAMPLE V

##### PBO/SWNT (80/20)

A composition of 20% single-wall carbon nanotubes (SWNT) and 80% polyphenylenebenzobisoxazole (PBO) was prepared as follows. Into the bottom of a 250-ml resin flask equipped with a mechanical stirrer, a nitrogen inlet and outlet, was placed 4.2612 g (0.02 mol) of 1,4-diaminoresorcinol dihydrochloride, 4.0605 g (0.02 mol) of terephthaloyl chloride, and 16.87g of phosphoric acid (85%). The resulting mixture was dehydrochlorinated under nitrogen atmosphere at 65°C for 16 hours. The temperature was then raised to 80°C and held for 4 hours. 0.94 g of purified SWNT (HiPco™ single-wall carbon nanotubes from Carbon Nanotechnologies, Inc., Houston, TX, purified according to the procedures given in I.W. Chiang, *et al.*, *J. Phys. Chem.*, Vol. 105, 2001, p. 8297) was added to the mixture. The mixture was heated at 100°C for 16 hours and then cooled to room temperature. 11.16g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to generate polyphosphoric acid (77% P<sub>2</sub>O<sub>5</sub>). The mixture was stirred for 2 hours at 80°C and then cooled to room temperature. 13.4g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to bring the polymer concentration to 10%. The mixture was heated at 160°C for 16 hours. As the temperature increased, stir opalescence began to occur at about 155°C. The mixture was finally heated to 190°C and held for an additional 4 hours. An aliquot of the polymer dope was precipitated in water, broken up with a blender, collected by suction filtration, washed with water and dried under reduced pressure (0.02 mmHg) at 100°C for 24 hours. An intrinsic viscosity of 13 dl/g was determined in methanesulfonic acid, at 30°C.

#### EXAMPLE VI

##### PBO Control

Polyphenylenebenzobisoxazole (PBO) was prepared as follows. Into the bottom of a 250-ml resin flask equipped with a mechanical stirrer, a nitrogen inlet and outlet, was placed 4.2612 g (0.02 mol) of 1,4-diaminoresorcinol dihydrochloride, 4.0605 g (0.02 mol) of terephthaloyl chloride, and 16.87g of phosphoric acid (85%). The resulting mixture was

dehydrochlorinated under nitrogen atmosphere at 65°C for 16 hours. The temperature was then raised to 80°C and held for 4 hours. The mixture was then heated at 100°C for 16 hours and then cooled to room temperature. 11.16g of P<sub>2</sub>O<sub>5</sub> was added to generate polyphosphoric acid (77% P<sub>2</sub>O<sub>5</sub>). The mixture was stirred for 2 hours at 80°C and cooled to room temperature. 13.4g of P<sub>2</sub>O<sub>5</sub> was added to bring the polymer concentration to 10%. The polymer mixture was heated at 160°C for 16 hours. As the temperature increased, stir opalescence began to occur at about 155°C. The mixture was finally heated to 190°C and held for an additional 4 hours. An aliquot of the polymer dope was precipitated in water, broken up with a blender, collected by suction filtration, washed with water and dried under reduced pressure (0.02 mmHg) at 100°C for 24 hours. An intrinsic viscosity of 12 dl/g was determined in methanesulfonic acid at 30°C.

#### EXAMPLE VII

##### Di-OH-PPBI/MWNT (95/5)

A composition of 5% multi-wall carbon nanotubes (MWNT) and 95% polydihydroxyphenylenepyridobisimidazole (Di-OH-PPBI) was prepared as follows. Into the bottom of a 250-ml resin flask equipped with a mechanical stirrer, a nitrogen inlet and outlet, was placed 5.3310 g (0.02 mol) of 2,3,5,6-tetraaminopyridine-trihydrochloride-monohydrate, 4.7004 g (0.02 mol) of 2,5-dihydroxyterephthaloyl chloride, and 11.66 g of phosphoric acid (85%). The resulting mixture was dehydrochlorinated under nitrogen atmosphere at 65°C for 16 hours. The temperature was then raised to 80°C and held for 4 hours. 0.26 g of multi-wall carbon nanotubes (Pyrograph PR-24-HT carbon nanofiber grade from Applied Sciences, Inc., Cedarville, OH) was added to the mixture. The mixture was heated at 100°C for 16 hours and then cooled to room temperature. 7.71 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to generate polyphosphoric acid (77% P<sub>2</sub>O<sub>5</sub>). The mixture was stirred for 2 hours at 80°C and then cooled to room temperature. 12.14 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to bring the polymer concentration to 14%. The mixture was heated at 165°C for 16 hours. As the temperature increased, stir opalescence began to occur at about 158°C. The mixture was finally heated to 190°C and held for an additional 4 hours. An aliquot of the polymer dope was precipitated in water, broken up with a blender, collected by suction filtration, washed with water and dried under reduced pressure (0.02 mmHg) at 100°C for 24 hours. An intrinsic viscosity of 18 dl/g was determined in methanesulfonic acid at 30°C.

## EXAMPLE VIII

## Di-OH-PPBI/SWNT (95/5)

A composition of 5% single-wall carbon nanotubes (SWNT) and 95% polydihydroxyphenylenepyridobisimidazole (Di-OH-PPBI) was prepared as follows. Into the bottom of a 250-ml resin flask equipped with a mechanical stirrer and a nitrogen inlet/outlet, was placed 5.3310 g (0.02 mol) of 2,3,5,6-tetraaminopyridine-trihydrochloride-monohydrate, 4.7004 g (0.02 mol) of 2,5-dihydroxyterephthaloyl chloride, and 11.66 g of phosphoric acid (85%). The resulting mixture was dehydrochlorinated under nitrogen atmosphere at 65°C for 16 hours. The temperature was then raised to 80°C and held for 4 hours. 0.26 g of purified SWNT (HiPco™ single-wall carbon nanotubes from Carbon Nanotechnologies, Inc., Houston, TX, purified according to the procedures given in I.W. Chiang, *et al.*, *J. Phys. Chem.*, Vol. 105, 2001, p. 8297) was added to the mixture. The mixture was heated at 100°C for 16 hours and then cooled to room temperature. 7.71 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to generate polyphosphoric acid (77% P<sub>2</sub>O<sub>5</sub>). The mixture was then stirred for 2 hours at 80°C and cooled to room temperature. 12.14 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to bring the polymer concentration to 14%. The mixture was then heated at 165°C for 16 hours. As the temperature increased, stir opalescence began to occur at about 158°C. The mixture was finally heated to 190°C and held for an additional 4 hours. An aliquot of the polymer dope was precipitated in water, broken up with a blender, collected by suction filtration, washed with water and dried under reduced pressure (0.02 mmHg) at 100°C for 24 hours. An intrinsic viscosity of 17 dl/g was determined in methanesulfonic acid at 30°C.

## EXAMPLE IX

## DIOH-PBI/MWNT (95/5)

A composition of 5% multi-wall carbon nanotubes (MWNT) and 95% polydihydroxyphenylenebenzobisimidazole (Di-OH-PBI) was prepared as follows. Into the bottom of a 250-ml resin flask equipped with a mechanical stirrer, a nitrogen inlet and outlet, was placed 5.6804 g (0.02 mol) of 1,2,4,5-tetraaminobenzene tetrahydrochloride, 4.7004 g (0.02 mol) of 2,5-dihydroxyterephthaloyl chloride, and 12.55 g of phosphoric acid (85%). The resulting mixture was dehydrochlorinated under nitrogen atmosphere at 65°C for 16 hours. The temperature was then raised to 80°C and held for 4 hours. 0.26 g MWNT (Pyrograph PR-24-HT carbon nanofiber grade from Applied Sciences, Inc., Cedarville, OH)

was added to the mixture. The mixture was heated at 100°C for 16 hours and then cooled to room temperature. 8.30 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to generate polyphosphoric acid (77% P<sub>2</sub>O<sub>5</sub>). The mixture was stirred for 2 hours at 80°C and then cooled to room temperature. 10.89 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to bring the polymer concentration to 14%. The mixture was heated at 145°C for 36 hours. As the temperature increased, stir opalescence began to occur at about 140°C. An aliquot of the polymer dope was precipitated in water, broken up with a blender, collected by suction filtration, washed with water and dried under reduced pressure (0.02 mmHg) at 100°C for 24 hours. An intrinsic viscosity of 17.5 dl/g was determined in methanesulfonic acid at 30°C.

#### EXAMPLE X

##### BBL/MWNT (95/5)

A composition of 5% multi-wall carbon nanotubes (MWNT) and 95% ladder polymer benzimidazobenzophenanthroline (BBL) was prepared as follows. Into the bottom of a 250-ml resin flask equipped with a mechanical stirrer, a nitrogen inlet and outlet, was placed 5.6804 g (0.02 mol) of 1,2,4,5-tetraaminobenzene tetrahydrochloride, 6.0842 g (0.02 mol) of 1,4,5,8-naphthalenetetracarboxylic acid, and 16.16 g of phosphoric acid (85%). The resulting mixture was dehydrochlorinated under nitrogen atmosphere at 65°C for 16 hours. The temperature was then raised to 80°C and held for 4 hours. 0.33 g of multi-wall carbon nanotubes (Pyrograph PR-24-HT carbon nanofiber grade from Applied Sciences, Inc., Cedarville, OH) was added to the mixture. The mixture was heated at 100°C for 16 hours and then cooled to room temperature. 10.69 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to generate polyphosphoric acid (77% P<sub>2</sub>O<sub>5</sub>). The mixture was stirred for 2 hours at 80°C and cooled to room temperature. 20.02 g of P<sub>2</sub>O<sub>5</sub> was added to the mixture to bring the polymer concentration to 12%. The mixture was then heated at 160°C for 16 hours. As the temperature increased, stir opalescence began to occur at about 160°C. The mixture was finally heated to 190°C and held for additional 4 hours. An aliquot of the polymer dope was precipitated in water, broken up with a blender, collected by suction filtration, washed with water and dried under reduced pressure (0.02 mmHg) at 100°C for 24 hours. An intrinsic viscosity of 20 dl/g was determined in methanesulfonic acid at 30°C.

#### EXAMPLE XI

##### PBO/SWNT (95/5) Fiber Formation

Fibers of the polymer composition of 5% single-wall carbon nanotubes (SWNT) and 95% polyphenylenebenzobisoxazole (PBO), as made by the procedure in Example III, were dry-jet wet spun using a piston driven spinning system manufactured by Bradford University Research Ltd. The polymer dope was first preheated to 50°C for about 15 minutes. The polymer dope was then formed into a cylindrical shape under dry nitrogen and transferred to the spinning cylinder. The polymer composition was heated at 100°C for about five hours before spinning. A 50- $\mu$ m stainless steel filter (from Anderson Wire Works, Inc.) filter was used in-line for fiber spinning and the spinneret diameter was 250  $\mu$ m. A 30-mm spinning cylinder was used with a 28-mm diameter piston. The length of the air gap was 10 cm and length of the coagulation bath was 75 cm. Spun fiber was washed in water for one week, vacuum dried at 80°C for 12 hours and subsequently heat-treated in a Thermolyne 21100 tube furnace at 400°C in nitrogen under tension for 2 minutes.

#### EXAMPLE XII

##### PBO/SWNT (90/10) Fiber Formation

Fiber formation with the polymer composition of 10% single-wall carbon nanotubes (SWNT) and 90% polyphenylenebenzobisoxazole (PBO), as made by the procedure in Example IV, was tried at different temperatures using dry-jet wet spinning with a piston driven spinning system manufactured by Bradford University Research Ltd. The polymer dope was heated to 100°C. Fiber could not be spun at this temperature because the thrust was too high. Attempts were also made to spin the fiber at 120°C as well as 130°C. Successful fiber spinning was conducted at 150°C using dry-jet wet spinning. A 50- $\mu$ m stainless steel filter (from Anderson Wire Works, Inc.) was used in-line for fiber spinning and the spinneret diameter was 250  $\mu$ m. 30 mm spinning cylinder was used with a 28-mm diameter piston. The length of the air gap was 10 cm and length of the coagulation bath was 75 cm. Spun fiber was washed in water for one week, vacuum dried at 80°C for 12 hours and subsequently heat-treated in a Thermolyne 21100 tube furnace in nitrogen at 400°C under tension for 2 minutes.

#### EXAMPLE XIII

##### PBO Control Fiber Formation

Fibers of polyphenylenebenzobisoxazole (PBO), as made by the procedure in Example VI, were dry-jet wet spun using a piston driven spinning system manufactured by Bradford University Research Ltd. The polymer dope was first preheated to 50°C for about 15 minutes. The polymer dope was then formed into a cylindrical shape under dry nitrogen and transferred to the spinning cylinder. The polymer was heated at 100°C for about five hours before spinning. A 50- $\mu$ m stainless steel filter (from Anderson Wire Works, Inc.) was used in-line for fiber spinning and the spinneret diameter was 250  $\mu$ m. A 30-mm spinning cylinder was used with a 28-mm diameter piston. The length of the air gap was 10 cm and length of the coagulation bath was 75 cm. Spun fiber was washed in water for one week, vacuum dried at 80°C for 12 hours and subsequently heat-treated in a Thermolyne 21100 tube furnace at 400°C in nitrogen under tension for 2 minutes.

#### EXAMPLE XIV

##### Fiber testing

Tensile modulus, tensile strength, and elongation to break were determined for the PBO-based fibers prepared according to Examples XI, XII and XIII, 95/5 PBO/SWNT, 90/10 PBO/SWNT and PBO control, respectively. The fibers were mounted on cardboard tabs. Tensile testing was performed on an Instron Universal Tensile Tester (Model 5567) at 2.54 cm gauge length at a strain rate of 2% per minute. Fiber diameters were measured using laser diffraction. About 20 samples of each fiber were tested. The data are given in Table 1.

Table 1 Mechanical Properties of PBO and PBO/SWNT composite fibers.

Fiber Sample	Tensile Modulus (GPa)	Tensile Strength (GPa)	Elongation to Break (%)
PBO Control (Example XIII)	138	2.6	2.0
PBO/SWNT (95/5) (Example XI)	156	3.2	2.3
PBO/SWNT (90/10) (Example XII)	167	4.2	2.8



The data show that tensile modulus, tensile strength, as well as elongation to break of PBO/SWNT (90/10) fiber are all higher than comparable measurements for the control PBO fiber by about 20, 60, and 40%, respectively. The average tensile strength values for the PBO control fibers varied between 1.8 and 2.6 GPa, while the average tensile strength values for the PBO/SWNT (90/10) fibers varied between 2.9 and 4.2. Thus, for various trials, a tensile strength increase of 40 to 60% was obtained by incorporating 10 wt% SWNT in PBO. The stress-strain curves for PBO/SWNT (90/10) and PBO control fibers are shown in Figure 1.

The coefficient of thermal expansion (CTE) was measured for PBO and PBO/SWNT (90/10) fibers. The CTE data for the PBO and PBO/SWNT (90/10) fibers, shown in Figure 2, are -6 and -4 parts per million (ppm) per °C, respectively. PBO/SWNT (90/10) also exhibits reduced high temperature creep (measured using a TA Instruments TMA 2940) as compared to the control PBO fiber, as, as shown in Figure 3. Thermal degradation for PBO/SWNT and PBO, conducted at 10°C/min using a TA Instruments TGA 2950, were comparable, as shown in Figure 4.

All of the compositions and methods disclosed and claimed herein can be made and executed without undue experimentation in light of the present disclosure. While the compositions and methods of this invention have been described in terms of preferred embodiments, it will be apparent to those of skill in the art that variations may be applied to the compositions and methods and in the steps or in the sequence of steps of the method described herein without departing from the concept, spirit and scope of the invention. More specifically, it will be apparent that certain agents which are both chemically and physiologically related may be substituted for the agents described herein while the same or similar results would be achieved. All such similar substitutes and modifications apparent to those skilled in the art are deemed to be within the spirit, scope and concept of the invention as defined by the appended claims.


## WHAT IS CLAIMED IS:

1. A composition comprising a rigid-rod polymer and carbon nanotubes.
2. The composition of claim 1 wherein the carbon nanotubes are selected from the group consisting of single-wall carbon nanotubes, multi-wall carbon nanotubes and a combination thereof.
3. The composition of claim 1 wherein the carbon nanotubes are present at a concentration in the range of about 0.1 wt% to about 50 wt% of the polymer.
4. The composition of claim 1 wherein the carbon nanotubes are present at a concentration in the range of about 1 wt% to about 30 wt% of the polymer.
5. The composition of claim 1 wherein the rigid-rod polymer is a liquid crystalline polymer.
6. The composition of claim 1 wherein the rigid-rod polymer comprises a benzobisazole polymer comprising a repeat group of the formula




wherein Y is -O-, -S- or -NR', wherein R' is selected from the group consisting of -H, alkyl having 1 to 4 carbon atoms, and an aromatic group having 1 or 2 aromatic rings.

7. The composition of claim 1 wherein the rigid-rod polymer comprises a para-ordered heterocyclic polymer comprising a repeat group of the formula






or




wherein Y is -S-, -O-, or -NR', and wherein R' is -H, an alkyl group having 1 to 4 carbon atoms or an aromatic group having 1 or 2 aromatic rings.

8. The composition of claim 1 wherein the rigid-rod polymer comprises a para-ordered heterocyclic polymer comprising a repeat group of the formula



or



wherein Y is -S-, -O-, -NR', n is 1 or 2, R is a hydroxyl group, a sulfo group or an alkyl group having 1 to 4 carbon atoms and R' is -H, an alkyl group having 1 to 4 carbon atoms or an aromatic group having 1 or 2 aromatic rings.

9. The composition of claim 8 wherein n is 1.

10. The composition of claim 9 wherein the R is -HSO<sub>3</sub>.


11. The composition of claim 9 wherein R is -CH<sub>3</sub>.

12. The composition of claim 8 wherein n is 2.


13. The composition of claim 12 wherein R is -CH<sub>3</sub>.

14. The composition of claim 12 wherein R is -OH.

15. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




5

16. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




10

17. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or


15




18. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




19. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




20. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or



21. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula



or




wherein R is -CH<sub>3</sub> and R' is -CH<sub>3</sub> or R is -CH<sub>3</sub> and R' is -H.


10

15


22. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




23. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a  
5 repeat group of the formula




or



10 24. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a  
repeat group of the formula




or




15

25. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a  
repeat group of the formula




or




wherein R is  $-\text{CH}_3$  and R' is  $-\text{CH}_3$  or R is  $-\text{CH}_3$  and R' is  $-\text{H}$ .

5

26. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




10

27. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or

15




28. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula

5




10 29. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




15

wherein R is  $-\text{CH}_3$  and R' is  $-\text{CH}_3$  or R is  $-\text{CH}_3$  and R' is  $-\text{H}$ .


30. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or



31. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




32. The composition of claim 1 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula






33. A fiber comprising a rigid-rod polymer and carbon nanotubes.
34. The fiber of claim 33 wherein the carbon nanotubes are selected from the group consisting of single-wall carbon nanotubes, multi-wall carbon nanotubes and a combination thereof.
35. The fiber of claim 33 wherein the carbon nanotubes are present at a concentration in the range of about 0.1 wt% to about 50 wt% of the polymer.
36. The fiber of claim 33 wherein the carbon nanotubes are present at a concentration in the range of about 1 wt% to about 30 wt% of the polymer.
37. The fiber of claim 33 wherein the rigid-rod polymer is a liquid crystalline polymer.
38. The fiber of claim 33 wherein the rigid-rod polymer comprises a benzobisazole polymer comprising a repeat group of the formula




wherein Y is -O-, -S- or -NR', wherein R' is selected from the group consisting of -H, alkyl having 1 to 4 carbon atoms, and an aromatic group having 1 or 2 aromatic rings.

39. The fiber of claim 33 wherein the rigid-rod polymer comprises a para-ordered heterocyclic polymer comprising a repeat group of the formula




or




wherein Y is -S-, -O-, or -NR', and wherein R' is -H, an alkyl group having 1 to 4 carbon atoms or an aromatic group having 1 or 2 aromatic rings.

40. The fiber of claim 33 wherein the rigid-rod polymer comprises a para-ordered heterocyclic polymer comprising a repeat group of the formula



or



wherein Y is -S-, -O-, -NR', n is 1 or 2, R is a hydroxyl group, a sulfo group or an alkyl group having 1 to 4 carbon atoms and R' is -H, an alkyl group having 1 to 4 carbon atoms or an aromatic group having 1 or 2 aromatic rings.

41. The fiber of claim 40 wherein n is 1.

42. The fiber of claim 41 wherein R is -HSO<sub>3</sub>.


43. The fiber of claim 41 wherein R is  $-\text{CH}_3$ .

44. The fiber of claim 40 wherein n is 2.


45. The fiber of claim 44 wherein R is  $-\text{CH}_3$ .

46. The fiber of claim 44 wherein R is  $-\text{OH}$ .

5 47. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




10

48. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or



15


49. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or

-33-


20




50. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




51. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




52. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or



53. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




wherein R is -CH<sub>3</sub> and R' is -CH<sub>3</sub> or R is -CH<sub>3</sub> and R' is -H.

10


54. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




55. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




56. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or



57. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




wherein R is  $-CH_3$  and R' is  $-CH_3$  or R is  $-CH_3$  and R' is  $-H$ .

5

58. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or



10


59. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula



or




15




60. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula

5



10 61. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




15


wherein R is  $-\text{CH}_3$  and R' is  $-\text{CH}_3$  or R is  $-\text{CH}_3$  and R' is  $-\text{H}$ .




62. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




63. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula



or



64. The fiber of claim 33 wherein the rigid-rod polymer is a polymer comprises a repeat group of the formula



65. A film comprising a rigid-rod polymer and carbon nanotubes.


66. The film of claim 65 wherein the carbon nanotubes are selected from the group consisting  
5 of single-wall carbon nanotubes, multi-wall carbon nanotubes and a combination thereof.

67. The film of claim 65 wherein the carbon nanotubes are present at a concentration in the  
range of about 0.1 wt% to about 50 wt% of the polymer.


68. The film of claim 65 wherein the carbon nanotubes are present at a concentration in the  
range of about 1 wt% to about 30 wt% of the polymer.

69. The film of claim 65 wherein the rigid-rod polymer is a liquid crystalline polymer.

70. The film of claim 65 wherein the rigid-rod polymer comprises a benzobisazole polymer  
comprising a repeat group of the formula




or




wherein Y is -O-, -S- or -NR', wherein R' is selected from the group consisting of -H,  
alkyl having 1 to 4 carbon atoms, and an aromatic group having 1 or 2 aromatic rings.

71. The film of claim 65 wherein the rigid-rod polymer comprises a para-ordered  
heterocyclic polymer comprising a repeat group of the formula




or




5 wherein Y is -S-, -O-, or -NR', and wherein R' is -H, an alkyl group having 1 to 4 carbon atoms or an aromatic group having 1 or 2 aromatic rings.

72. The film of claim 65 wherein the rigid-rod polymer comprises a para-ordered heterocyclic polymer comprising a repeat group of the formula



or



15

wherein Y is -S-, -O-, -NR', n is 1 or 2, R is a hydroxyl group, a sulfo group or an alkyl group having 1 to 4 carbon atoms and R' is -H, an alkyl group having 1 to 4 carbon atoms or an aromatic group having 1 or 2 aromatic rings.

20 73. The film of claim 72 wherein n is 1.

74. The film of claim 73 wherein R is -HSO<sub>3</sub>.

75. The film of claim 73 wherein R is -CH<sub>3</sub>.


76. The film of claim 72 wherein n is 2.

77. The film of claim 76 wherein R is  $-\text{CH}_3$ .


78. The film of claim 76 wherein R is  $-\text{OH}$ .

79. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat

5 group of the formula




10 80. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




15


81. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




20




82. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




83. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




84. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or



85. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




wherein R is -CH<sub>3</sub> and R' is -CH<sub>3</sub> or R is -CH<sub>3</sub> and R' is -H.


86. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




87. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat  
5 group of the formula




or




10 88. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat  
group of the formula




or



15 89. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat  
group of the formula




or




wherein R is  $-\text{CH}_3$  and R' is  $-\text{CH}_3$  or R is  $-\text{CH}_3$  and R' is  $-\text{H}$ .

5

90. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or



10


91. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula



or


15






92. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula

5




10 93. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




15

wherein R is  $-\text{CH}_3$  and R' is  $-\text{CH}_3$  or R is  $-\text{CH}_3$  and R' is  $-\text{H}$ .


94. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




95. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or




96. The film of claim 65 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula



97. The method for preparing a composite comprising a rigid-rod polymer and a carbon nanotube, comprising polymerizing a rigid-rod polymer in the presence of carbon nanotubes.
98. The method of claim 97 wherein the polymer is a liquid crystalline polymer.
99. The method of claim 97 wherein the polymerizing is by polycondensation.
100. The method of claim 97 wherein the carbon nanotubes are selected from the group consisting of single-wall carbon nanotubes, multi-wall carbon nanotubes and a combination thereof.
101. The method of claim 97 wherein the rigid-rod polymer comprises a benzobisazole polymer comprising a repeat group of the formula




or




wherein Y is -O-, -S- or -NR', wherein R' is selected from the group consisting of -H, alkyl having 1 to 4 carbon atoms, and an aromatic group having 1 or 2 aromatic rings.

102. The method of claim 97 wherein the rigid-rod polymer comprises a para-ordered heterocyclic polymer comprising a repeat group of the formula



or




5


wherein Y is  $-S-$ ,  $-O-$ , or  $-NR'$ , and wherein  $R'$  is  $-H$ , an alkyl group having 1 to 4 carbon atoms or an aromatic group having 1 or 2 aromatic rings.

10

103. The method of claim 97 wherein the rigid-rod polymer comprises a para-ordered heterocyclic polymer comprising a repeat groups of the formula



or



15

wherein Y is  $-S-$ ,  $-O-$ ,  $-NR'$ , n is 1 or 2, R is a hydroxyl group, a sulfo group or an alkyl group having 1 to 4 carbon atoms and  $R'$  is  $-H$ , an alkyl group having 1 to 4 carbon atoms or an aromatic group having 1 or 2 aromatic rings.


20

104. The method of claim 103 wherein n is 1.


105. The method of claim 104 wherein the R is  $-HSO_3$ .

106. The method of claim 104 wherein R is  $-CH_3$ .


107. The method of claim 103 wherein n is 2.
108. The method of claim 107 wherein R is  $-\text{CH}_3$ .
109. The method of claim 107 wherein R is  $-\text{OH}$ .
110. The method of claim 97 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or



- 10 111. The method of claim 97 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula




or



112. The method of claim 97 wherein the rigid-rod polymer is a polymer comprising a repeat group of the formula

5



113. The method of claim 97 further comprising spinning the composite into a fiber.
114. The method of claim 113 wherein the fiber is spun by the dry-jet wet technique.
115. The method of claim 113 further comprising washing and drying the fiber.
116. The method of claim 113 further comprising heat treating the fiber.
117. An article comprising the fiber of claim 33.
118. The article of claim 117 wherein the article is selected from the group consisting of vehicle armor, bullet-proof vests, body armor and armor for a structure.
119. The article of claim 117 wherein the article is an element of a ballistic protection system.
120. An article comprising the film of claim 65.
121. The article of claim 120 wherein the article is selected from the group consisting of vehicle armor, bullet-proof vests, body armor and armor for a structure.
122. The article of claim 120 wherein the article is an element of a ballistic protection system
123. An article comprising the composition of claim 1.
124. The article of claim 123 wherein the article is selected from the group consisting of structural building components and structural machine components.

25




Figure 1




Figure 2




Figure 3






Figure 4

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/27370

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C01B31/02 A61K9/70 B05D3/10 G03F7/038 C08K3/04  
C08L77/00 C08K5/01 C01B31/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 C01B A61K B05D G03F C08K C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	WO 02 16257 A (SMALLEY RICHARD E ; UNIV RICE WILLIAM M (US); SMITH KEN A (US); COL) 28 February 2002 (2002-02-28) page 4, line 17 - page 6, line 10 page 8, line 14 - line 26 page 11, line 38 - page 12, line 16 abstract; claims 1,8,25,64	1-124
X	US 6 203 814 B1 (OGATA NAOYA ET AL) 20 March 2001 (2001-03-20) column 4, line 55 - column 5, line 21 column 7, line 1 - line 9 abstract; claim 1; examples 1-19 --- -/--	1-124

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the International filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the International filing date but later than the priority date claimed

- \*T\* later document published after the International filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- \*G\* document member of the same patent family

Date of the actual completion of the International search

30 October 2002

Date of mailing of the International search report

11/11/2002

Name and mailing address of the ISA

European Patent Office, P.B. 6818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Glomm, B

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/27370

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 100 03 011 A (RIKEN WAKO ; SUMITOMO BAKELITE CO (JP)) 31 August 2000 (2000-08-31) page 3, line 37 - page 5, line 21 page 17, line 16 - line 21 abstract; claims 1-7; examples 1-11 -----	1-124
X	US 5 997 832 A (WONG ERIC ET AL) 7 December 1999 (1999-12-07) column 2, line 28 - line 37 column 3, line 16 - line 52 column 5, line 12 - line 18 column 8, line 16 - line 23 abstract; claims 1-5; examples 1-8 -----	1-124
X	EP 0 680 995 A (HOECHST AG) 8 November 1995 (1995-11-08) page 2, line 50 - page 3, line 34 page 3, line 57 - line 58 abstract; claims 1-21 -----	1-124
X	US 5 276 085 A (KASOWSKI ROBERT V ET AL) 4 January 1994 (1994-01-04) column 1, line 29 - line 39 column 3, line 17 - line 24 abstract; claims 1-5; example 2 -----	1-124
X	DE 42 07 246 A (BASF AG) 9 September 1993 (1993-09-09) page 2, line 1 - line 38 page 5, line 53 - page 6, line 5 abstract; claims 1-6; examples 1-5 -----	1-124

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 02/27370

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0216257	A	28-02-2002	AU 8665501 A	04-03-2002
			WO 0216257 A2	28-02-2002
			US 2002048632 A1	25-04-2002
			US 2002046872 A1	25-04-2002
			US 2002068170 A1	06-06-2002
US 6203814	B1	20-03-2001	AU 707522 B2	15-07-1999
			AU 4598096 A	26-06-1996
			CA 2207282 A1	13-06-1996
			EP 0796403 A1	24-09-1997
			JP 11502494 T	02-03-1999
			KR 263027 B1	01-08-2000
			US 2002086335 A1	04-07-2002
			WO 9618059 A1	13-06-1996
			US 6362011 B1	26-03-2002
			US 5866434 A	02-02-1999
DE 10003011	A	31-08-2000	JP 2000214585 A	04-08-2000
			JP 2000338668 A	08-12-2000
			DE 10003011 A1	31-08-2000
US 5997832	A	07-12-1999	AU 6187798 A	22-09-1998
			WO 9839251 A1	11-09-1998
EP 0680995	A	08-11-1995	DE 4411756 A1	19-10-1995
			EP 0680995 A1	08-11-1995
			EP 0852246 A2	08-07-1998
			JP 7278431 A	24-10-1995
US 5276085	A	04-01-1994	US 5296543 A	22-03-1994
DE 4207246	A	09-09-1993	DE 4207246 A1	09-09-1993